



## DKV.4171

### *Positive connection: cationic locking*

If you are using usual waterborne coatings, wood stains dissolve from the substrate and lead to a colour change. With our DKV.4171 we have the solution! The cationic nature of this resin helps to lock stains in the primer preventing migration to the surface. The waterborne DKV.4171 locks stains, dries fast and is eco-friendly. In addition, this resin offers a good adhesion to wood, old coats and mineral substrates.

#### **Unique properties**

- Locks wood bleeds without problems
- Locking properties against all types of stain and dirt
- Good wet adhesion
- Suitable for interior and exterior applications

#### **Environment-friendly**

- Contains neither APEO nor plasticiser
- Not EUH 208 labelled

#### **Typical applications**

- Wood stain locking primers
- Locking primer against nicotine, soot and water stains

#### **Technical properties**

Resin base	Acrylate / VeoVa
Solids content	39–41 %
Density	approx. 1 g/ml at 20 °C
Stabilizer system	cationic
Viscosity	1200–1800 mPa·s at 20 °C
pH-value	5.0–6.0
Particle size	170 nm
MFFT	<5 °C
Frost resistance	no

*White isulating primer based on DKV.4171*  
*Starting formulation 4171-IG01-01*

	<b>Raw materials</b>	<b>Quantity</b>	<b>Function</b>	<b>Supplier</b>
1	Water	143.0		
2	Disperbyk-2012	6.0	Wetting and dispersing agent	BYK-Chemie GmbH
3	Tego Foamex 815 N	1.0	Defoamer	Evonik Industries AG
4	Kronos 2190	160.0	Pigment	Kronos International Inc.
5	Dorkafill Pro_Void	55.0	Filler	Gebrüder Dorfner GmbH & Co.
6	Finntalc MO5SL	10.0	Filler	Mondo Minerals
7	Blanc Fixe N	65.0	Filler	Sachtleben Chemie GmbH
8	Aerosil R 972	1.0	Anti-setting agent	Evonik Industries AG
<b>9</b>	<b>DKV.4171</b>	<b>550.0</b>	<b>Resin</b>	<b>VANORA AG</b>
10	Tafigel PUR 41	7.0	Thickener	Münzing Chemie GmbH
11	Tafigel PUR 61	0.5	Thickener	Münzing Chemie GmbH
12	Formic acid (10 %)	1.5	Acid	Diverse
		1000.0		

**Mixture instruction**

- Pos. 1-3 Submit  
Pos. 4-8 Add during agitation, disperse for at least 20 minutes  
Pos. 9 Add during agitation, stir for 5 minutes  
Pos. 10-11 Premix, add during agitation, stir for 10 minutes  
Pos. 12 Set pH to 5.0-6.0

**Technical data**

Viscosity Brookfield at approx. 20 °C (Spindle 6, 100UpM) 2560 mPa.s  
pH 6.0

**Suitable raw materials**

Dispersing agent: Disperbyk-2012, Edaplan 492, Tego Dispers 740 W, EFKA 4550  
Defoamer: Tego Foamex 815 N, BYK-1711, Agitan 700, Drewplus TS-4385  
Thickener: Tafigel PUR 41, Acrysol RM-825, Coapur 975 W, BYK-425  
Cosolvent: Butylglykol, Dowanol DPnB, Butyldiglykol, Texanol