

# DXA.4081

## Technical Data Sheet

### Description

DXA.4081 is an aqueous polymer dispersion based on Acrylate, VOC- and APEO-free.

### Suggested usage

DXA.4081 is a resin for the production of low-odour and solventless coatings. The dispersion is used in indoor and outdoor applications for paints, varnishes, plasters, crack bridging coatings, roof coatings, wood primers and basement floor paints.

### Processing

DXA.4081 is readily miscible with other components with standard mixing equipment. The dispersion can be processed with most commercial fillers, particularly suitable are PU-fillers. You can use different commercial products for defoaming. The right grade and concentration must be determined by experiment. DXA.4081 may be mixed with other dispersions in various ratios. Owing to the wide range of products available, however, compatibility and storage stability tests are vital.

### Technical data

Solids content	48-50 %
Density	approx. 1 g/ml
Stabilizer system	polymer
Viscosity (Brookfield)	100-800 mPa·s
pH value	6.5-7.5
Particle size	300 nm
MFFT	5 °C
Frost resistance	thawable

### Film properties

Water absorption (24 h)	7 %
Tensile strength at break	11 N/mm <sup>2</sup>
Elongation at break	1000 %
Glass transition temperature (T <sub>g</sub> )	0 °C
Water resistance	good

### Safety

Not a hazardous material in the sense of current legislation. Please follow the instructions on the Material Safety Data Sheet.

### Delivery form

120 kg drum, 1000 kg container and tank car

### Storage

The dispersion is already preserved against attack by microorganisms. This protection applies only to transport and unopened containers. For further adequate protection during continued storage in opened containers and storage tanks, appropriate preservatives should be added. Our resins should not be stored for longer than 12 months at temperatures from 5 to 30 °C prior to processing. Protect against frost and strong sunlight.

### Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our longstanding experience with the recommended applications under the specified conditions. Material, processing and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that VANORA AG technical support service be consulted first. VANORA AG general sales and delivery terms and conditions shall apply.