

WS.45.D

Technical Data Sheet

Description

WS.45.D is an aqueous polymer dispersion based on VAc / VeoVa™, VOC- and APEO-free.

Suggested usage

WS.45.D is a resin for the production of low-odour and solventless coatings. The dispersion is primarily used for indoor and outdoor applications for white washes and plasters, stucco and modelling compounds.

Processing

WS.45.D is readily miscible with other components with standard mixing equipment. The dispersion can be processed with most commercial additives, fillers and titanium dioxide. The right grade and concentration must be determined by experiment. WS.45.D may be mixed with other dispersions in various ratios. Owing to the wide range of products available, however, compatibility and storage stability tests are vital.

Technical data

Solids content	41-44 %
Density	approx. 1 g/ml
Stabilizer system	polyvinyl alcohol
Viscosity (Brookfield)	2000-12000 mPa·s
pH value	2.5-4.0
Particle size	2500 nm
MFFT	2 °C
Frost resistance	no

Film properties

Water absorption (24 h)	approx. 25 %
Tensile strength at break	4 N/mm ²
Elongation at break	450 %
Glass transition temperature (Tg)	-1 °C

Safety

Not a hazardous material in the sense of current legislation. Please follow the instructions on the Material Safety Data Sheet.

Delivery form

120 kg drum, 1000 kg container and tank car

Storage

The dispersion is already preserved against attack by microorganisms. This protection applies only to transport and unopened containers. For further adequate protection during continued storage in opened containers and storage tanks, appropriate preservatives should be added. Our resins should not be stored for longer than 12 months at temperatures from 5 to 30 °C prior to processing. Protect against frost and strong sunlight.

Guarantee

We guarantee the consistency and faultless quality of this product, manufactured in accordance with ISO quality standards, which has been developed on the basis of our longstanding experience with the recommended applications under the specified conditions. Material, processing and application conditions may significantly influence product properties. Pre-application tests by the user are therefore essential. For non-specified applications or deviations in application conditions, we recommend that VANORA AG technical support service be consulted first. VANORA AG general sales and delivery terms and conditions shall apply.